




1. Trugloss-FSC-Royal Blue Opaque

2. 11P20

3. HG60



Facestock

One side semi-gloss coated face-stock. The semi-gloss face-stock has a bright, clear and smooth printing surface.

| | | |
|---------------------|----|----------|
| Basis weight (g/m2) | 92 | ISO 536 |
| Caliper (µm) | 76 | ISO 534 |
| Opacity (%) | 99 | ISO 2471 |

Adhesive

11P20 is a tackified, acrylic pressure sensitive adhesive (PSA). Engineered to have high tack value to both high and low energy surface substrates.

| | | |
|--------------------------|---------------|-------------|
| Loop Tack (N/25mm) | 12 | FINAT No. 9 |
| Peel adhesion (N/25mm) | 12 | FINAT No. 1 |
| Minimum application temp | 0°C | |
| Service temperature | -20°C to +60C | |

Release liner

A super calendared honey glassine, silicone coated one side

| | | |
|---------------------|----|----------|
| Basis weight (g/m2) | 55 | ISO 536 |
| Caliper (µm) | 48 | ISO 534 |
| Transparency (%) | 50 | ISO 2469 |

Conversion and Printing

Suitable to be used with a variety of printing techniques. Including flexographic, screen and litho.

Our Warranty

The technical information, recommendations and statements are based on data believed to be reliable but do not constitute a guarantee or warranty. The information is given without legal responsibility. The customer should test under own condition to ensure the product is suitable for their own requirements. Tullis Russell products are warranted to be free of defects in material for a period of up to one year from the date of shipment. Tullis Russell will not be responsible for claims beyond the replacement value of the defective product nor in any way be liable or responsible for consequential or incidental damages. No waiver, alteration, addition or modification of the foregoing conditions shall be valid unless made in writing and signed by a director of Tullis Russell. Other warranty, express or implied, or whether of merchantability or fitness for a particular use or otherwise, shall be excluded. Shelf life: 12 months at 22C and 50% RH.