


LABELSTOCK TRUDIGITAL® JET HIGH GLOSS WHITE 90/11P20/WG60





Facestock

A super high gloss inkjet paper for high definition printing. The print is instantly dry. Suitable for high speed inkjet systems.

Basis weight (g/m²)	95	ISO 536
Caliper (µ)	106	ISO 534

Release liner

A super calendared white glassine, silicone coated one side.

57	ISO 536
53	ISO 534
48	DIN 53147
	53

Conversion and Printing

Specially formulated for use with all common commercial high-speed inkjet printing systems.

Adhesive

11P20 is a tackified, acrylic pressure sensitive adhesive (PSA). Engineered to have high tack value to both high and low energy surface substrates.

Loop Tack (N/25mm)	12	FINAT No 9 (glass)
Peel adhesion (N/25mm)	12	FINAT No 1 (glass)
Minimum application temp	0°C	
Service temperature	-20°C to +60°C	

Regulatory approval:

The adhesive may stand in direct contact with dry, moist and such kind of fatty foodstuffs to which a correction factor of at least 5 can be applied according to the commission regulation (EU) No. 10/2011.

The adhesive is compliant to FDA 175.105

Our Warrantv

Cur warranty The technical infonnation, recommendations and statements are based on data believed to be reliable but do not constitute a guarantee or warranty. The information is given without legal responsibility. The customer should test under own condition to ensure the product is suitable for their own requirements. Tullis Russell products are warranted to be free of defects in material for a period of up to one year from the date of shipment. Tullis Russell will not be responsible for claims beyond the replacement value of the defective product nor in any way be liable or responsible for consequential or incidental damages. No waiver, alteration, addition or modification of the foregoing conditions shall be valid unless made in writing and signed by a Director of Tullis Russell. Other warranty, express or implied, or whether of merchantability or fitness for a particular use or otherwise, shall be excluded. Shelf life: 12 months at 22[°]C and 50% RH.

